

DESCRIPTION & ADVANTAGES

IMAGING PAPERS WALLPAPER

WALLPAPERSOL PERSOMURAL 195

satin 3259 195 g/m²

matt 3280 195 g/m²

High quality, non woven wallpaper coated with a solvent ink receptive layer, which offers a good colour gamut and high scratch resistance. Due to the properties of this wallpaper, no additional protection is needed and it can be hung with standard non woven wallpaper paste.



Advantages

- The coating and prints are water-resistant - no liquid lamination required
- Quick dry
- Smooth surface
- Wide gamut and high colour rendering
- High opacity for good coverage
- High dimensional stability and wet strength resistance
- Can be applied with standard paste for non woven wallpaper
- Covers small cracks
- Easy to remove
- PVC-free
- Fire Classification: C-s1,d0 (ISO EN 13501-1:2007)
- COV / VOC 3259
- COV / VOC 3280
- CE-Declaration of Performance 3259 / CE-Label 3259
- CE-Declaration of Performance 3280 / CE-Label 3280

GENERAL TIPS & STORAGE

To maintain the high quality of this fleece, it should be stored and converted in a climate of 30 – 65 % relative humidity and at temperatures of 10 – 30 °C (50 – 86 °F).

After pasteing the wall with a standard wallpaper paste, the wallpaper can be hung just like all other fleece wallpapers. Thanks to its structure, it is easy to remove again and requires no additional protection.

SIZES, APPLICATIONS, PROPERTIES

Finished Rolls

Width	Length	Width	Length	Core	No. rolls / pallet	Min. quantity / order	No. rolls / box
24.0 "	167.3 ´	61.0 cm	51.0 m	3 "ø	24	12	1
36.0 "	167.3 ´	91.4 cm	51.0 m	3 "ø	24	12	1
42.0 "	167.3 ´	106.7 cm	51.0 m	3 "ø	24	12	1
44.0 "	167.3 ´	111.8 cm	51.0 m	3 "ø	24	12	1
50.0 "	167.3 ´	127.0 cm	51.0 m	3 "ø	24	12	1
60.0 "	167.3 ´	152.4 cm	51.0 m	3 "ø	24	12	1

Applications



Print technologies



Properties



Other sizes may be available upon request.

physical properties

satín 3259 195 g/m²

Weight (Total) [gsm]	195	ISO 536
Thickness (total) [microns]	290	ISO 534
Whiteness (CIE, D65/2°) [%]	70	CIELab System
Opacity (TAPPI)	> 91	TAPPI T425
Chromaticity (D65 / 10°)	L* 96,0 a* -0,3 b* 3	DIN 6174

matt 3280 195 g/m²

Weight (Total) [gsm]	195	ISO 536
Thickness (total) [microns]	340	ISO 534
Chromaticity (D65 / 10°)	L* 97 a*-0,5 b*3,5	DIN 6174
Opacity [%]	91	ISO 2471
Whiteness (CIE, D65/2°) [%]	75	CIELab System

PRINTER COMPATIBILITIES

Printer	3259	3280
Hewlett Packard DJ L65500 Latex ink	😊😊	😊😊😊
Hewlett Packard DJ L25500 / 26500 / 28500 - Latex 260 / 280	😊😊	😊😊😊
Hewlett Packard Scitex LX 600		😊😊😊
Hewlett Packard Scitex LX 800 / LX 820 / LX 850		😊😊😊
Hewlett Packard Latex 310 / 330 / 360 / 3000	😊😊	😊😊
Hewlett Packard Latex 280 / 820 / 850	😊😊	😊😊
ColorSpan DisplayMaker 72S	😊😊😊	
ColorSpan Display Maker 72 UVR	😊😊😊	
Epson Stylus Pro GS6000 UltraChrome GS	😊😊😊	😊😊😊
Epson SureColor SC-30600 / 50600 / 70600		😊😊😊
Roland SolJet SJ540 / SC540 SJ 740 / SC740		😊😊😊
Roland SC-500 Permasol S	😊😊😊	😊😊😊
Roland VersaCAMM SP-300i / SP-540i	😊😊😊	😊😊😊
Roland VersaCAMM VP-300i / VP-540i	😊😊😊	😊😊😊
Roland VS 540 / VS 640	😊😊😊	😊😊😊
Roland CJV 30	😊😊😊	😊😊😊
Roland SolJET PRO4 XR-640	😊😊😊	😊😊😊
Mimaki JV400SUV Serie	😊😊😊	😊😊😊
Océ CS9360 / CS935	😊😊😊	😊😊😊
Last update	10/20/2015	10/20/2015
Legend		
Excellent	😊😊😊	
Good	😊😊	
Fair	😊	

Datasheet

Online Datasheet **satin 3259** 195 g/m²

Online Datasheet **matt 3280** 195 g/m²